NOTES:

1. SUBSTRATE: FUSED SILICA

2. COATING (APPLY ACROSS CLEAR APERTURE)

S1: 355nm HR Coating R(ABS) > 99.8% @ 355nm @ 45° AOI R(AVG) > 99.5% FROM 351-358nm @ 45° AOI


DAMAGE THRESHOLD


PULSED: 6 J/cm², 20ns, 20 Hz @ 355nm

CW: 1MW/cm² @ 355nm

$\frac{1}{3}$ FINE GRIND SURFACE

4. ROHS COMPLIANT





FOR INFORMATION ONLY: DO NOT MANUFACTURE PARTS TO THIS DRAWING

SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

	\$1	\$2		
SHAPE	PLANO	PLANO		
SURFACE QUALITY	20-10	20-10 Ø22.50		
CLEAR APERTURE	31.81 x 22.50			
SURFACE FLATNESS	λ/20			
BEVEL	PROTECTIVE AS NEEDED	PROTECTIVE AS NEEDED		

		G	Edmund Optics®		
THIRD ANGLE TITLE		TITLE	25mm, 1/20 WAVE, 355nm, HR CTD HYP, HT RA, FS PRISM		
ALL DIMS IN	mm	DWG NO	37651	SHEET 1 OF 1	